

# **Armeen TM-97**

# Tallowalkylamines

Tallow alkyl amines, 97% minimum purity

# **Specifications**

Amine number	209-217 mg KOH/g
Color	≤ 3 (1963) Gardner
lodine value	38-54 g l₂/100 g
Moisture	≤ 0.5 %
Neutralization equivalent	258-269 g/eq
Primary Amine	≥ 97 %
Secondary Amine	≤ 3 %

# Characteristics

Appearance	Solid at 25°C
Boiling point	260-350 (760 mm Hg) °C
Clear point	43 °C
Equivalent mass	267 g/eq
Flash point	≥100
HLB	8.2 (Davies scale 0-40)
Melting point	40 °C
Pour point	35 °C

### Notes:

Typical Data are based on our own measurements or derived from the literature. They do not constitute part of the delivery specification.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

ARMEEN is a registered trademark in many countries.

## Contact Us

#### USA and Canada

Global Headquarters
Chicago
USA
+1 312 544 7000
ansc-cs@nourvon.com

#### China

Regional Headquarters Shanghai China +86 21 2220 5000 surfactants.asia@nouryon.com

#### Europe

Regional Headquarters
Stenungsund
Sweden
+46 303 850 00
surfactants.europe@nouryon.com

#### South East Asia

Regional Headquarters
Singapore
+65 6635 5183
surfactants.asia@nouryon.com

#### South America

Regional Sales Office Itupeva Brazil +55 11 4591 8938

