


# Butanox D-50

Methyl ethyl ketone peroxide, solution in dimethyl phthalate and TXIB



Butanox D-50 is a multipurpose catalyst used for curing gel coats and promoted unsaturated polyester resins at room temperature. Low-hydrogen peroxide content reduces gel-coat porosity and provides improved curing of vinyl ester resins.

**CAS number**  
1338-23-4

**EINECS/ELINCS No.**  
215-661-2

**TSCA status**  
listed on inventory

## Specifications

Appearance, 20-25°C	Clear liquid
Total active oxygen	8.8-9.0 %

## Characteristics

Density, 20 °C	1.1 g/cm <sup>3</sup>
----------------	-----------------------

## Applications

Butanox D-50 is an ideal multipurpose catalyst for the room temperature cure of gel coats and promoted unsaturated polyester resins. Butanox D-50 has a low hydrogen peroxide content, which reduces gel coat porosity and provides improved curing of vinyl ester resins. Butanox D-50 also has a high MEKP monomer content which provides reduced cure times in some resin systems. Additional end-use information is available in various application sheets or directly from your Nouryon representative.

## Thermal stability

Organic peroxides are thermally unstable substances, which may undergo self-accelerating decomposition. The lowest temperature at which self-accelerating decomposition of a substance in the original packaging may occur is the Self-Accelerating Decomposition Temperature (SADT). The SADT is determined on the basis of the Heat Accumulation Storage Test.

SADT	60°C (140°F)
------	--------------

Method	The Heat Accumulation Storage Test is a recognized test method for the determination of the SADT of organic peroxides (see Recommendations on the Transport of Dangerous Goods, Manual of Tests and Criteria - United Nations, New York and Geneva).
--------	--

## Storage

Due to the relatively unstable nature of organic peroxides a loss of quality can be detected over a period of time. To minimize the loss of quality, Nouryon recommends a maximum storage temperature (Ts max. ) for each organic peroxide product.

Ts Max.	30°C (86°F)
---------	-------------

Note	When stored under these recommended storage conditions Butanox D-50 will remain within the Nouryon specifications for a period of at least 3 months after delivery.
------	---

## Packaging and transport

Butanox D-50 is packed in non-returnable, 1 gallon polyethylene containers of 8 lb net weight (4 per case) and in 5 gallon polyethylene containers of 40 lb net weight. Both packaging and transport meet the international regulations. For the availability of other packed quantities contact your Nouryon representative. Butanox D-50 is classified as Organic peroxide type D; liquid; Division 5. 2; UN 3105; PG II.

## Safety and handling

Keep containers tightly closed. Store and handle Butanox D-50 in a dry well-ventilated place away from sources of heat or ignition and direct sunlight. Never weigh out in the storage room. Avoid contact with reducing agents (e. g. amines), acids, alkalis and heavy metal compounds (e. g. accelerators, driers and metal soaps). Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of Butanox D-50. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at [nouryon.com/sds-search](http://nouryon.com/sds-search).

## Major decomposition products

Carbon dioxide, Water, Acetic acid, Formic acid, Propionic acid, Methyl ethyl ketone

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Butanox is a registered trademark of Nouryon Functional Chemicals B.V. or affiliates in one or more territories.

## Contact Us

Polymer Catalysts Americas  
[polymer.amer@nouryon.com](mailto:polymer.amer@nouryon.com)

Polymer Catalysts Europe, Middle East, India and Africa  
[polymer.emeia@nouryon.com](mailto:polymer.emeia@nouryon.com)

Polymer Catalysts Asia Pacific  
[polymer.apac@nouryon.com](mailto:polymer.apac@nouryon.com)

The Nouryon logo consists of a stylized orange 'N' followed by the word 'ouryon' in a lowercase, sans-serif font, all in orange.