

# DIBAL-H

## Diisobutylaluminum hydride

DIBAL-H is an aluminium alkyl used as reducing agent in organic synthesis.

CAS number  
1191-15-7

EINECS/ELINCS No.  
214-729-9

TSCA status  
listed on inventory

Molecular weight  
142.2

### Composition

Aluminum	<sup>b</sup> 18.8 wt%
Diisobutylaluminum hydride	<sup>a</sup> ≥ 97.0 wt%
Other R <sub>3</sub> Al	<sup>a</sup> -- wt%
Triisobutylaluminum	<sup>a</sup> ≤ 3.0 wt%

### Characteristics

Appearance	Clear, colorless liquid
Boiling point, 1 mm Hg	114 °C
Density, 30 °C	0.797 g/cm <sup>3</sup>
Melting point	-80 °C
Solubility	Soluble in aromatic and saturated aliphatic and cycloaliphatic hydrocarbons
Stability to air	Ignites upon exposure
Stability to water	Reacts violently, may ignite upon contact
Viscosity, 30 °C	13.5 mPa.s

### Thermochemical properties

Heat of vaporization $\Delta H_v$ , NBP / 1 bar	297 J/g (71 cal/g)
Heat of hydrolysis, 25 °C	3523 J/g (842 cal/g)
Specific heat, 57 °C	2.146 J/g.°C (0.513 cal/g.°C)
Heat of formation $\Delta H_f^\circ$ , 25 °C / 1 bar	-402 kJ/mole (-96 kcal/mole)
Heat of combustion $\Delta H_c^\circ$ , 25 °C	-6410 kJ/mole (-1532 kcal/mole)

#### Notes:

<sup>a</sup> Calculated from gas chromatographic analysis of hydrocarbons and hydrogen obtained by hydrolysis. <sup>b</sup> Determined by titration of aqueous hydrolyzate. NBP = Normal Boiling Point i.e. temperature at which the vapor pressure is 760 mm Hg (1 bar).

### Applications

DIBAL-H is used as a cocatalyst in the Ziegler-Natta polymerization of olefins and as a reducing agent in organic synthesis.

## Storage

DIBAL-H and its solutions are stable when stored under a dry, inert atmosphere and away from heat. DIBAL-H decomposes slowly above about 120°C. Decomposition products include hydrogen, isobutylene and elemental aluminum.

## Packaging and transport

DIBAL-H and its solutions are available worldwide in cylinders and portable tanks. In North America only, DIBAL-H is also available in tank trailers and rail cars. Containers are fabricated from carbon steel and are equipped with dip tubes for top discharge and all connections are located in the vapor space. Both packaging and transport meet the international regulations.

## Safety and handling

DIBAL-H ignites upon exposure to air and reacts violently with water. Hydrocarbon solutions of DIBAL-H may also ignite upon exposure to air. Solutions of DIBAL-H in ethers have been known to decompose violently. DIBAL-H and its solutions must be handled under a dry, inert atmosphere, e. g. nitrogen or argon. Water must be scrupulously removed from process equipment prior to putting it into metal alkyls service. Failure to do so may result in an explosion. Products of complete combustion of DIBAL-H and its solutions are aluminum oxide, carbon dioxide and water. DIBAL-H causes severe burns to the skin and eyes. It is imperative that proper personal protective equipment be worn when handling DIBAL-H. Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of DIBAL-H. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at [nouryon.com/sds-search](http://nouryon.com/sds-search).

## Additional information

Availability: DIBAL-H is a commercial product available as the neat pyrophoric liquid and as pyrophoric and nonpyrophoric solutions in a variety of hydrocarbon solvents. Consult your Nouryon representative for further information.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

## Contact Us

**Polymer Catalysts Americas**  
[polymer.amer@nouryon.com](mailto:polymer.amer@nouryon.com)

**Polymer Catalysts Europe, Middle East, India and Africa**  
[polymer.emeia@nouryon.com](mailto:polymer.emeia@nouryon.com)

**Polymer Catalysts Asia Pacific**  
[polymer.apac@nouryon.com](mailto:polymer.apac@nouryon.com)

The Nouryon logo consists of a stylized orange 'N' followed by the word 'ouryon' in a lowercase, sans-serif font, all in orange.