

# Ketjenblack EC-600JD powder

## Carbon black

Pure electroconductive carbon black with high porosity and specific surface, specifically used for batteries and fuel cells .

CAS number  
1333-86-4

EINECS/ELINCS No.  
215-609-9

TSCA status  
listed on inventory

### Specifications

200 mesh Pass	≥ 98.0 %
325 mesh Pass	80.0 %
Apparent bulk density	17-50 kg/m <sup>3</sup>
Appearance	Black powder
Moisture	≥ 1.0 %
Pore volume, DBP	440-510 ml/100g

### Applications

Ketjenblack EC-600JD powder is a very pure carbon black extremely suitable for antistatic and electroconductive applications. Due to its unique morphology and the extremely high surface area of approx. 1400 m<sup>2</sup>/g (BET), only one sixth the amount of Ketjenblack EC-600JD powder is needed compared to conventional electroconductive blacks in order to achieve the same conductivity. The extreme low loading of Ketjenblack EC-600JD powder allows easier processing for those compounds sensitive to filler addition, thus minimizing loss in mechanical and rheological properties. Ketjenblack EC-600JD powder when thoroughly dispersed with the polymer significantly increases the conductivity of the resulting compound.

### Storage

Nouryon recommends to store Ketjenblack EC-600JD powder in a dry place away from direct sunlight. The packaging can be damaged if exposed to direct sunlight for more than 30 minutes.

#### Note

When stored under these recommended storage conditions, Ketjenblack EC-600JD powder will remain within the Nouryon specifications for a period of at least one year after delivery.

### Packaging and transport

The standard packaging is a 4 kg net in a paper bag with plastic lining. The vent consists of a small plastic valve which contains HDPE, NBR and cellulosic parts, which are not readily dispersed during compounding. Due to this we strongly advise not to put the Ketjenblack EC-600JD powder including the bag into the mixing system. A full pallet carries 320 kg net. Both packaging and transport meet the international regulations. For the availability of other packed quantities contact your Nouryon representative. Ketjenblack EC-600JD powder is classified as a non-hazardous good according to national and international transport regulations.

## Safety and handling

Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of Ketjenblack EC-600JD powder. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at [nouryon.com/sds-search](http://nouryon.com/sds-search).

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Ketjenblack is a registered trademark of Nouryon Chemicals B. V. or affiliates in one or more territories.

## Contact Us

For Polymer Catalysts EMEA inquiries:  
[polymer.emeia@nouryon.com](mailto:polymer.emeia@nouryon.com)

For Polymer Catalysts Asia Pacific inquiries:  
[polymer.apac@nouryon.com](mailto:polymer.apac@nouryon.com)

For HPMO Americas inquiries:  
[metalorganicsNA@nouryon.com](mailto:metalorganicsNA@nouryon.com)

For Polymer Catalysts Americas inquiries:  
[polymer.amer@nouryon.com](mailto:polymer.amer@nouryon.com)

The Nouryon logo consists of a stylized orange 'N' followed by the word 'ouryon' in a lowercase, sans-serif font, all in orange.