

MMAO-3A 7 wt% AL in Heptane

Modified Methylaluminoxane, type 3A ^a

Heptane solutions of MMAO-3A are used as co-catalysts in the polymerization of olefins and other monomers via single-site catalysts. Can also be used for tri and tetramerization processes

CAS number
146905-79-5

EINECS/ELINCS No.
931-024-8

TSCA status
listed on inventory

Characteristics

Appearance	Clear, colorless to slightly hazy liquid
Density, 25 °C	0.723 g/cm ³
Solubility	Soluble in aromatic and saturated aliphatic hydrocarbons
Stability to air	May ignite upon exposure
Stability to water	Reacts violently
Viscosity, 25 °C	0.6 mPa.s

Notes:

^a Composition covered under US Patent 5,041,584. For more information on aluminoxanes, see the nouryon technical bulletin entitled Properties of Aluminoxanes from Nouryon. ^b Data for heptane solution containing 7% aluminum; this corresponds to an MMAO-3A concentration of about 18%. ^c Calculated from gas chromatographic analysis of hydrocarbons and hydrogen obtained by hydrolysis. ^d Other components include hydrocarbons, such as ethane, propane, isobutylene and n-butane. ^e Determined by titration of aqueous hydrolyzate. ^f Determined by the pyridine titration method.

Applications

Heptane solutions of MMAO-3A are used as cocatalysts in polymerization of olefins and other monomers via single-site catalysts

Storage

MMAO-3A in heptane is stable when stored under a dry, inert atmosphere and away from heat. MMAO-3A in heptane is significantly more stable to long-term storage than solutions of conventional polymethylaluminoxane. However, if MMAO-3A is stored for a prolonged period above 30°C we advise to shield the storage and/or dosage tank in order to protect them from direct sunlight.

Packaging and transport

Heptane solutions of MMAO-3A are available worldwide in cylinders and portable tanks. In North America only, MMAO-3A in heptane is also available in tank trailers and rail cars. Containers are fabricated from carbon steel and are equipped with dip tubes for top discharge and all connections are located in the vapor space. Both packaging and transport meet the international regulations

Safety and handling

Heptane solutions of MMAO-3A may ignite upon exposure to air and react violently with water. Heptane solutions of MMAO-3A must be handled under a dry, inert atmosphere, e.g. nitrogen or argon. Water must be scrupulously removed from process equipment prior to putting it into metal alkyls service. Failure to do so may result in an explosion. Products of complete combustion of heptane solutions of MMAO-3A are aluminum oxide, carbon dioxide and water. Heptane solutions of MMAO-3A cause severe burns to the skin and eyes. It is imperative that proper personal protective equipment be worn when handling heptane solutions of MMAO-3A. Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of heptane solution of MMAO-3A. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at <https://polymerchemistry.nouryon.com>

Additional information

Availability: MMAO-3A in heptane is a commercial product (typically containing ~7% aluminum). The product is not available neat. Consult your Nouryon representative for further information.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Contact Us

Europe, Middle East, India and Africa
polymerchemistry.nl@nouryon.com

Asia Pacific
polymerchemistry.ap@nouryon.com

Americas
polymerchemistry.na@nouryon.com

The Nouryon logo consists of a stylized orange 'N' followed by the word 'ouryon' in a lowercase, sans-serif font. The 'N' is significantly larger and more prominent than the rest of the text.