


Perkadox BTW-50

Dibenzoyl peroxide, paste, 50% in dipropylene glycol dibenzoate and water



Perkadox BTW-50 is the preferred BPO paste for unsaturated polyester & vinyl ester resins.

CAS number
94-36-0

EINECS/ELINCS No.
202-327-6

TSCA status
listed on inventory

Molecular weight
242.2

Active oxygen content
peroxide
6.61%

Concentration
3.20-3.37%

Specifications

Appearance	White homogeneous paste
Assay	48.5-51.0 %

Characteristics

Density, 20 °C	1.200 g/cm ³
Viscosity, 20 °C	thixotropic paste mPa.s

Applications

Perkadox BTW-50 is a paste containing 50% dibenzoyl peroxide without phthalate for the curing of unsaturated polyester resins at ambient and elevated temperatures. At temperatures up to 80°C, Perkadox BTW-50 should be used in combination with an aromatic tertiary amine accelerator, above 80°C the use of an accelerator is not required. Perkadox BTW-50 has primarily been developed for the putty market. For non filled systems, Perkadox CH 50X or Perkadox 40E are better applicable with respect to miscibility with the UP resin. Perkadox BTW-50 shows a very good chemical and physical stability and is therefore very suitable for tube filling. The curing system Perkadox BTW-50/amine accelerator shows a very fast cure that is hardly influenced by humidity and fillers. Even at low temperatures a relatively good cure will be obtained. A disadvantage may be the yellow color and poor light resistance of the moulded product.

Thermal stability

Organic peroxides are thermally unstable substances, which may undergo self-accelerating decomposition. The lowest temperature at which self-accelerating decomposition of a substance in the original packaging may occur is the Self-Accelerating Decomposition Temperature (SADT). The SADT is determined on the basis of the Heat Accumulation Storage Test.

SADT	50°C (122°F)
Emergency temperature (T _e)	45°C (113°F)
Control temperature (T _c)	40°C (104°F)
Method	The Heat Accumulation Storage Test is a recognized test method for the determination of the SADT of organic peroxides (see Recommendations on the Transport of Dangerous Goods, Manual of Tests and Criteria - United Nations, New York and Geneva).

Storage

Due to the relatively unstable nature of organic peroxides a loss of quality can be detected over a period of time. To minimize the loss of quality, Nouryon recommends a maximum storage temperature (T_s max.) for each organic peroxide product.

T _s Max.	25°C (77°F)
Note	When stored under the recommended storage conditions, Perkadox BTW-50 will remain within the Nouryon specifications for a period of at least 3 months after delivery.

Packaging and transport

In North America Perkadox BTW-50 is packed in 45 lb plastic pails. In other regions the standard packaging is plastic pails for 20 kg peroxide. Both packaging and transport meet the international regulations. For the availability of other packed quantities contact your Nouryon representative. Perkadox BTW-50 is classified as Organic peroxide type E; solid; Division 5.2; UN 3108.

Safety and handling

Keep containers tightly closed. Store and handle Perkadox BTW-50 in a dry well-ventilated place away from sources of heat or ignition and direct sunlight. Never weigh out in the storage room. Avoid contact with reducing agents (e.g. amines), acids, alkalis and heavy metal compounds (e.g. accelerators, driers and metal soaps). Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of Perkadox BTW-50. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at <https://polymerchemistry.nouryon.com>.

Major decomposition products

Carbon dioxide, benzoic acid, benzene, diphenyl, phenyl benzoate

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Perkadox is a registered trademark of Nouryon Chemicals B.V. or affiliates in one or more territories.

Contact Us

Europe, Middle East, India and Africa
polymerchemistry.nl@nouryon.com

Asia Pacific
polymerchemistry.ap@nouryon.com

Americas
polymerchemistry.na@nouryon.com

The Nouryon logo consists of a stylized orange 'N' followed by the word 'ouryon' in a lowercase, sans-serif font, all in orange.