

Witbreak GT-756

Ortho ester polymer

Witbreak GT-756 is a polymerized polyol

Specifications

Cloud point	76-79 (5g product in 25 ml 25% butyldiglycol) °C
Water content	≤ 0.5 %

Characteristics

Active content	78-82 %
Appearance	Solid at 20°C
Butyl diglycol	18-22 %
Color	brownish
Density	1025 kg/m ³ at 20°C
Flash point	≥ 100°C
pH	8.5-10.5 (1% in water)
Pour point	26 °C
Relative Solubility Number	19-20
Solubility in other solvents	Soluble in butyl diglycol
Viscosity	261 mPa.s at 50°C
Solubility: Solubility in water	Soluble

Notes:

Typical Data are based on our own measurements or derived from the literature. They do not constitute part of the delivery specification.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

WITBREAK is a registered trademark in many countries. For more information, please visit our website at www.nouryon.com.

The logo for Nouryon, featuring a stylized blue 'N' followed by the word 'ouryon' in a blue sans-serif font.